

Biofunctionalization of PDMS-based microfluidic systems

Cesar Fernández-Sánchez (✉ cesar.fernandez@imb-cnm.csic.es)

Chemical Transducers Group

Andreu Llobera (✉ andreu.llobera@imb-cnm.csic.es)

Chemical Transducers Group

Bergoi Ibarlucea

Chemical Transducers Group

Stefanie Demming

Institut für Mikrotechnik, Technische Universität Braunschweig

Stephanus Büttgenbach

Institut für Mikrotechnik, Technische Universität Braunschweig

Method Article

Keywords: PDMS, biofunctionalization, microfluidics, lab-on-a-chip

Posted Date: November 29th, 2011

DOI: <https://doi.org/10.1038/protex.2011.271>

License:  This work is licensed under a Creative Commons Attribution 4.0 International License.

[Read Full License](#)

Abstract

Three simple approaches for the selective immobilization of biomolecules on the surface of poly(dimethylsiloxane) (PDMS) microfluidic systems that do not require any specific instrumentation, are described and compared. They are based in the introduction of hydroxyl groups on the PDMS surface by direct adsorption of either polyethylene glycol (PEG) or polyvinyl alcohol (PVA) as well as by a liquid-based oxidation step. The hydroxyl groups are then silanized using a silane containing an aldehyde end-group that allows the surface to interact with a primary amine moiety of the biomolecule structure to be immobilized. The entire process takes 4.5h. The required steps can be characterized in less than 15 hours by contact angle measurements, X-ray photoelectron spectroscopy (XPS) and atomic force microscopy (AFM). The performance of the biofunctionalization process can be assessed by using peroxidase enzyme as a model biomolecule. Its correct immobilization and stability is easily tested by developing an analytical approach for hydrogen peroxide (H₂O₂) detection in the biofunctionalized microfluidic system and carrying out analytical measurements for a period of up to two months. The full version of this protocol as a Word file has been upload and can be accessed from "this link":http://www.nature.com/protocolexchange/system/uploads/2007/original/ibarlucea_2011.docx?1322233604

Introduction

Microfluidic systems have been highly evolving with the simultaneous development of polymer materials. Polymer technology has been key in the realization and definition of the so-called Lab-on-a-Chip (LoC) concept. The current high impact of LoC systems is partly due to the application of polymers such as polycarbonate (PC), poly(methyl methacrylate) (PMMA), SU-8 and poly(dimethylsiloxane) (PDMS), which have made them more versatile while in turn have enabled reducing their fabrication cost and time. PDMS (Figure 1a) is a cheap material that polymerizes at low temperatures¹. It is optically transparent in a very wide wavelength range, from ultra-violet (UV) to the Near-Infrared (NIR)². This last property makes the material compatible with many optical detection methods. It is also compatible with biological studies, since it is non-permeable to water, non toxic and permeable to gases. PDMS is an elastomer with a 2.5 MPa Young modulus when prepared with a 10:1 ratio of a base:curing agent³. Cast molding of the as-prepared PDMS provides a rapid fabrication of microsystems with resolution down to 0.1 μm⁴. The resulting systems can easily be sealed to many different substrates³. When LoCs are fabricated with PDMS, low-cost systems can be obtained with the potential of being highly sensitive. However, this polymer has a disadvantage: biomolecules and other macromolecules easily adsorb non-specifically to it, thus hindering its application for chemical sensing. This disadvantage can easily be turned into an advantage as it can easily be modified in order to avoid that process or, by contrast, to selectively immobilize different molecules². These surface modification processes are usually needed for the application of PDMS-based microsystems to (bio)chemical analysis. The aims of the modification are diverse and include from the minimization of the biomolecular adsorption, to the increase of the hydrophilic/hydrophobic character of the surface. Some processes are directed to bind a biologically

active molecule that changes the lubricity of the surface⁵ or provides the material with the capacity to give a selective answer to a specific target analyte by binding antibodies⁶ or enzymes⁷.

Biofunctionalization of PDMS surfaces can be carried out following two different strategies: physical adsorption and covalent modification. The first one is very simple but, due to the weak interactions between the adsorbed molecules and the surface, the modifications are unstable both thermally and mechanically. Also, solvolytic processes can also occur. Covalent modification can overcome these problems and provide more stable modifications⁸. It is carried out by the initial introduction of hydroxyl groups (-OH) on the PDMS surface, which can further be modified by a silanization process. These hydroxyl groups react with silane molecules to form covalent Si-O-Si (siloxane) bonds. Different functional groups, to which the biomolecules can be covalently attached, are introduced on the surface depending on the chosen silane⁹. In this context, PDMS surfaces have been treated with oxygen plasma¹⁰ or UV/ozone¹¹, in order to make the surface hydrophilic by replacing the surface methyl groups, bound to the Si atom within the PDMS structure, by silanol groups (Si-OH). These new groups tend to chemically interact with other functional groups, allowing to selectively modify the surface. Silanol groups can be useful as an initial step in the PDMS surface modification for covalently binding enzymes, as Yasukawa *et al.* did⁷. They immobilized glucose oxidase on a PDMS layer after a hydrophilization step using a plasma process and further silanization, with the aim of fabricating a glucose sensor. Sandison *et al.* made also use of a plasma and silanization process to immobilize antibodies on a PDMS column for protein purification applications¹². But this process also has some drawbacks: the modification is temporal because the plasma oxidized surface progressively recovers its hydrophobicity. It also requires special instrumentation and cannot be applied in the microfluidic channels of LoCs¹³. This means that alternative processes must be found to selectively modify PDMS surfaces, which were easy to implement and could be applied in channels embedded in PDMS matrices.

The previously mentioned UV/ozone treatment could be an alternative process. The modification consists in firstly generating ozone from molecular oxygen by 185 nm wavelength light exposition and then photodissociating it to atomic oxygen under 254 nm wavelength light exposure. This oxygen abstracts hydrogen from the backbone of PDMS and silanol (Si-OH) structures are formed on it, becoming a hydrophilic surface¹⁴. This treatment is slower than a plasma activation process¹⁵ but it facilitates a much deeper modification without cracking or mechanical weakening side-effects¹¹. This fact enables its application to the microchannels. But, as pointed out before, the process is reversible, and PDMS surface eventually recovers its hydrophobicity after exposure to air for a few hours.

Chemical Vapour Deposition (CVD) can also be used to create polymer coatings on PDMS microchannels, as Chen and Lahann did for the eventual deposition of poly(4-benzoyl-p-xylylene-co-p-xylylene) films. A light reactive coating film of carbonyl groups was obtained, which was exposed to UV light in order to generate the free radicals that could react with poly(ethylene oxide) (PEO) and create PEO-functionalized regions that avoided the adsorption of fibrinogen¹⁶.

Silanol groups can also be obtained on PDMS surfaces by using sol-gel methods. Silica nanoparticles can be created in a PDMS piece by mixing it in a tetraethyl orthosilicate (TEOS) sol-gel precursor and then incubating it in an ethylamine catalyzing solution and heating it¹⁷. Glasslike layers can also be formed on a PDMS surface by applying the same sol-gel technique with transition metal sol-gel precursors¹⁸. However, these sol-gel methods are time consuming and therefore the production costs increase.

An acidic solution containing hydrogen peroxide (H_2O_2) can also be pumped inside the microchannels, which oxidizes the PDMS surface and creates silanol groups¹³. The process should be carefully controlled since an excess of acidity could lead to a loss of optical transparency of the PDMS.

Physical adsorption methods can also be applied for PDMS microchannel modification. These methods are applied to suppress electroosmotic flow in capillary electrophoresis and to avoid nonspecific binding of proteins. The hydrophobic parts of molecules can be physisorbed onto the PDMS surface while the hydrophilic parts keep exposed to the buffer, thus changing the surface properties of the PDMS. A coating process of polymers that contain hydrophobic and hydrophilic parts can be achieved by simply incubating the surface with the aqueous coating solution¹⁹. The so-called Layer by Layer (LbL) technique can also be carried out by electrostatic adsorption of positively and negatively charged alternating layers²⁰.

Here, the details of the protocol used in a previous work²¹ for different liquid-based surface chemical biofunctionalization methods are provided. The developed methods can easily be performed in standard chemical and biological laboratories avoiding the need of special instrumentation. Both physical adsorption and covalent modification methods are analyzed. On one hand, physical adsorption of two different polymers containing hydroxyl groups, such as polyethylene glycol (PEG) or polyvinyl alcohol (PVA) (figure 1b) enable the further silanization of the surface for the introduction of chemical functional groups and the eventual covalent immobilization of the bioreceptor. In some applications, as Yu *et al* did²², the aim of the PVA immobilization was to avoid the non-specific binding of proteins. Other groups used PEG instead of PVA, since it offers the same advantage^{23,24}. In the present application, the objective is totally different. These polymers are used as anchoring points for further silanization and final protein receptor immobilization. On the other hand, a covalent modification approach was tested based on the chemical oxidation of the PDMS surface that generates silanol groups (figure 1c) onto which a silanization process and further immobilization of the protein receptor are carried out, as above. This chemical oxidation protocol was already described by Sui *et al.* for creating hydroxyl groups that could be used as anchoring points for the immobilization of other molecules¹³. A deep structural characterization of the resulting modified surfaces is carried out. The analytical performance and the stability of the modified surfaces following the different methods are also tested using a PDMS-based photonic LoC (PhLoC) microsystem consisting of a hollow Abbe prism transducer configuration²⁵.

Experimental design

Modification of the PDMS surfaces

As it can be seen in Figure 2, the proposed three approaches for PDMS surface modification are based on the introduction of hydroxyl (-OH) groups and further silanization. PDMS surfaces were cleaned with ethanol and deionized water (DI H₂O). For the modification shown in Figure 2A, the PDMS surfaces were incubated in a PEG solution and left to adsorb. For the modification in Figure 2B, they were incubated in a PVA solution and left to adsorb. The backbone of these two polymers is able to physisorb from aqueous solutions to hydrophobic surfaces²⁶. The third approach was carried out by a chemical oxidation process with an acidic solution containing DI H₂O, HCl and H₂O₂¹³ (Figure 2C). After each of these steps, the surfaces were rinsed with DI H₂O and dried.

For the previously mentioned silanization process, the modified PDMS systems were incubated in 11-triethoxysilyl undecanal (TESU) and triethylamine (TEA) containing ethanol solutions. Then the surfaces were thoroughly rinsed with ethanol and dried. The TEA induces a highly nucleophilic oxygen in the -OH group that readily interacts with the chosen silane²⁷ having its ethoxy groups previously hydrolyzed. In this way, the silane molecules covalently bound to the surface (Figure 3).

Characterization of the PDMS surfaces

For the characterization process, flat PDMS surfaces were modified. The techniques used for this characterization were contact angle measurements, XPS and AFM.

Contact angle measurements were carried out with the sessile drop method. Images with a high contrast should be obtained with the camera of the goniometer, with as less light reflections as possible in the drop. If these conditions are hold, the software is able to automatically detect the shape of the drop and measure the contact angle.

XPS analysis was carried out on an Axis Ultra-DLD spectrometer, using a [monochromatized Al K \$\alpha\$ source](#) (1486.6 eV). Signals were deconvoluted with the software provided by the manufacturer, using a weighted sum of Lorentzian and Gaussian component curves after background subtraction. The binding energies were referenced to the internal standard C 1s (284.9 eV).

Atomic force microscopy topographic and phase images of the modified surfaces were taken with a Veeco Nanoscope Dimension 3100, working in tapping mode and using phosphorous doped n-type silicon tips (Micromasch, San Jose, CA, USA).

Reagents

- Poly(dimethylsiloxane) (PDMS) Sylgard 184 elastomer kit (Dow Corning)
- Polyvinyl alcohol 99% (PVA, molecular weight: 89,000-98,000g) (Sigma-Aldrich Co., cat. no. 341584)
- Polyethylene glycol (PEG, molecular weight: 12,000g) (Sigma-Aldrich Co., cat. no. 81285)
- Triethylamine 99% (TEA) (Sigma-Aldrich Co., cat. no. T0886) ! CAUTION Corrosive, Highly flammable
- 11-triethoxysilyl undecanal

90% TESU (ABCR GmbH & Co. KG, cat. no. AB152514) **CAUTION** Irritant ****REAGENT SETUP**** PVA solution: dissolve 25 mg in 25 mL DI H₂O. **? TROUBLESHOOTING** High temperature (60 °C) and stirring is needed to dissolve it. PEG solution: dissolve 25 mg in 25 mL DI H₂O. TESU solution: dilute 50 µL TESU and 50 µL TEA in 2.5 mL ethanol 99.5%. **CAUTION** Avoid the vapors coming from TEA by preparing the solution mix in a fume hood.

Equipment

• Automatic pipettes with disposable tips • Krüss Easydrop contact angle meter and DS1 analysis software (Krüss GmbH) • Axis Ultra-DLD spectrometer (Kratos Analytical Ltd) • Atomic Force Microscope: Veeco Nanoscope Dimension 3100 (Veeco) • AFM tips (Micromasch): n-type silicon tip (phosphorous doped) (NSC15/AIBS)

Procedure

Modification of the PDMS surfaces

1 | Clean flat PDMS surfaces: first with ethanol 96% and then with DI H₂O. **? TROUBLESHOOTING.** Flat PDMS surfaces are used for easier characterization of the resulting modifications.

2 | Create hydroxyl groups on the PDMS surface. Select the appropriate chemistry protocol:

A. Modification with PEG: immerse the PDMS in a 1 mg/ml PEG solution in DI H₂O. Leave to react for 1 hour. Then rinse with DI H₂O and dry with N₂.

B. Modification with PVA: immerse the PDMS in a 1 mg/ml PVA solution in DI H₂O. Leave to react for 1 hour. Then rinse with DI H₂O and dry with N₂.

C. Chemical oxidation: immerse the PDMS in an acidic solution containing DI H₂O, 37% HCl and 30% H₂O₂ in a 5:1:1 (v/v/v) ratio¹⁸. Then rinse with DI H₂O and dry with N₂. **? TROUBLESHOOTING.** This step can generate bubbles on the PDMS surface. Try to avoid them as far as possible by stirring the media. **CAUTION** Avoid the HCl vapors by carrying out this step in a fume hood. Use gloves, since apart from the acidic conditions of the liquid mixture, a direct contact with H₂O₂ could lead to a whitish irritating skin color.

3 | Create aldehyde groups on the PDMS surface by incubating them in a 99.5% ethanol solution containing 2% TESU and 2% TEA for 1 hour. Then rinse with 99.5% ethanol and dry them at 80°C for 2 hours. **CAUTION** Avoid the vapors coming from TEA by preparing the solution mix in a fume hood. **? TROUBLESHOOTING.** This step should be done in a closed container and using enough solvent to avoid the total evaporation of the liquid. It should be carried out in an inert atmosphere like nitrogen or argon without humidity presence.

■ **PAUSE POINT** After this step, systems can be stored overnight at 4°C in carbonate buffer pH 8.

Characterization of the modified PDMS surfaces

4 | Measure the contact angle with a contact angle meter: deposit a drop of water on the modified PDMS surfaces and compare the angle formed between the drop and the surface to the angle formed using a non-modified PDMS surface. Make several drops and calculate the mean value of the angle and its standard deviation. **? TROUBLESHOOTING.** Try to always use the same drop size. Try to obtain pictures with a high contrast to facilitate the automatic detection of the drop shape by the software of the contact angle meter. There should only appear one drop in each picture acquired by the camera. If there are more drops, the software could understand that the other drops form part of the drop that should be detected.

5 | Make an XPS analysis of the modified and non-modified PDMS surfaces. Use a monochromatized Al K α source or similar (1486.6 eV). Deconvolute the signals using a weighted sum of Lorentzian and Gaussian component curves after background subtraction.

6 | Obtain topographic and phase images by using an atomic force microscopy in tapping mode. In this mode, the cantilever oscillates up and down at its resonance frequency. The interaction between the tip and the surface when they come close causes a decrease of the oscillation amplitude, and the control system changes the height of the cantilever to maintain this amplitude constant. In phase images, changes in phase oscillations give information about the different type of materials that can be found on the surface. Topographic images give information about the surface roughness.

? TROUBLESHOOTING

Try to avoid an excess of contact between the tip and the surface because PDMS is a soft material and its deformation caused by the tip could appear in the pictures as noise. By contrast, if the distance between the surface and the tip is too large, a flat surface could be recorded.

Timing

Steps 1-3 Modification of the PDMS surfaces: 4h 30 minutes Steps 4-6: Characterization of the modified PDMS surfaces: 30 minutes for the contact angle measurements, 7 hours for the XPS analysis, 7 hours for the AFM.

Troubleshooting

Troubleshooting advices are presented in Table 1

Table 1| Troubleshooting table.

Step	Problem	Possible reason	Solution
2 B	PVA does not dissolve correctly	The needed time, temperature or stirring has not been applied	The solution should be left for 30 min at 60 °C with enough stirring using a magnetic stirrer (the revolutions per minute should be experimentally considered by the performer)
2 C	PDMS becomes white during the chemical oxidation	HCl concentration is too high or oxidation time is too long	Decrease the HCl concentration or oxidation time
3	The surface appears totally dry after the required incubation time	The solvent evaporates	Use more solvent and a closed container.
4	The shape of the drop is not correctly detected by the software of the contact angle meter	There may be too many light reflections or more drops on the surroundings	Try to use the correct light conditions to avoid reflections in the drop. There should only appear one drop in each acquired picture
5	Unexpected bonds or elements are found on the XPS analysis	The sample is contaminated	Preserve the samples in inert atmosphere (N ₂ or Ar) until the XPS analysis
6	There is too much noise in the AFM picture	The PDMS deforms when the tip of the AFM touches it	Increase the distance between the surface and the tip
6	The surface in the AFM picture is completely flat	The distance between the tip and the surface is too large	Decrease the distance between the surface and the tip

Anticipated Results

This protocol allows the selective and stable modification of PDMS substrates with biomolecules containing primary amine groups.

The processes described do not require any specific instrumentation, thus enabling the easy and rapid implementation in chemical and biological laboratories that work with PDMS-based microfluidic systems.

Structural characterization of the modified PDMS surfaces

Three different approaches were chosen for the modification of PDMS with the aim of providing different densities of hydroxyl groups on the surface and studying the influence on the immobilization of proteins and their eventual analytical performance. A higher density was expected for the PVA adsorption comparing to the PEG adsorption, due to the nature of their chemical structure. The conditions for the chemical oxidation process were set by an optimization study. It could be seen that a higher concentration

of hydrogen peroxide and HCl or longer incubation times degraded the PDMS surface too much. The step for the introduction of aldehyde groups was the same for all the procedures. This molecule enables the one-step covalent immobilization of the enzyme.

Contact angle measurements provided a rapid estimation of the degree of modification after each step by simply measuring the hydrophobic/hydrophilic character of the modified surface. Given the hydrophobic nature of the PDMS but the hydrophilic nature of groups sequentially introduced on its surface, a steady decrease in the water contact angle was expected. Once hydroxyl groups were introduced by PVA adsorption, a clear change from the 114.57° contact angle of the native PDMS to 102.47° of the PVA-modified surface was measured. The value found in the native PDMS was similar to that reported in previous studies²⁸. This decrease was not observed after the PEG adsorption. This is likely to be related to the lower density of hydroxyl groups that PEG provides. PEG only presents two hydroxyl groups at both ends of its chain, while PVA contains these groups all along its whole linear structure. The higher amount of introduced hydroxyl groups should facilitate the incorporation of a higher number of silane molecules during the silanization step. This step also gave rise to another change in the contact angle value when working with the PVA-modified surfaces, which decreased to 96.9° . However no difference was observed in the PEG-modified surfaces, which also suggests a low density of silane molecules on the PDMS surface and in turn corroborates the above-mentioned assumption that the number of silanol groups introduced by this modification approach is rather low. Also, no changes in the contact angle values were obtained following each step of the chemical oxidation approach. Again, this slight chemical oxidation process may give rise to a low density of silanol groups and of silane molecules on the PDMS surface. The values were plotted in a bar graph, which can be found in Figure 4.

A more in depth study of the surface modification processes was carried out by XPS analysis. With this technique an identification and rough estimation of the density of the introduced groups during the modification steps can be done. The percentage values of the different atoms present on the PDMS surface were extracted from the XPS survey scan. They are shown in Table 2. The carbon percentage increased after the PVA adsorption, from 43.38% to 51.74%, while the Si content decreased from 36.90% to 27.05%. This was a consequence of the adsorption of PVA molecules on the PDMS surface. The changes were not so clear in the surfaces prepared by the other procedures. High resolution spectra of the C1s region were recorded for the detection of the new peaks formed by the introduced groups. The deconvolution of the C1s region showed that new peaks appeared after each PDMS modification step (Figures 5, 6 and 7). The non-modified PDMS presented one peak with a binding energy of 284.90 eV. This peak corresponded to the carbon atom of the methyl group. After the different steps that introduce hydroxyl groups on the surface, a new peak appeared with an energy of 286.50 eV, which corresponded to the C–O bond. Both PVA and PEG molecules contain this bond, but PEG has it in lower quantities, so it gave a smaller signal in the spectra, as expected. C–O bonds are not expected in the PDMS surface modified by the chemical oxidation procedure and just Si–OH groups should be detected. However, it is reported that oxidation of PDMS could give rise to hydroxyl groups that are bound to the carbon atom of the methyl groups²⁹. This could be the reason of the presence of the C–O peak after the

chemical oxidation step. Additionally, another peak was observed in all the surfaces after the silanization step. This peak corresponded to the C=O bond that is part of the aldehyde group of the applied functional silane. The highest signal was again found in the surfaces corresponding to the PVA adsorption procedure. These results reflect that the PVA modification process is more effective for the introduction of chemical functional groups on the surface of PDMS, in accordance with the contact angle measurement.

AFM studies were also carried out to the resulting surfaces after each modification steps. The recorded topographic and phase images (Figure 8) showed that the native PDMS surface was flat and structurally and chemically homogeneous. After each modification step, the modified surfaces exhibited slight or dramatic variations depending on the applied procedure. After PVA adsorption, branch-like structures could be observed (also shown in Figure 8). These branches might be related to the linear structure of the PVA polymer chains that were adsorbed to the PDMS. After the silanization process with TESU, a honeycomb-like structure was observed (last two images of Figure 8). In this case, a polymerization process could have taken place among the TESU molecules, forming a layer that covered the entire surface.

The adsorption of PEG did not seem to affect the PDMS substrates (Figure 9). By contrast, after the silanization process, homogeneously dispersed dots appeared on the surface. These might be TESU-based structures generated at the specific positions where isolated hydroxyl groups belonging to the adsorbed PEG molecules were located. The reason for the differences between the TESU layer in the PVA modified surface and the PEG modified one may be that PEG contains only hydroxyl groups at the ends of its chain, as mentioned above.

In the case of the surfaces modified by chemical oxidation, AFM images (Figure 10) showed an increase in the roughness compared to the non-modified PDMS surface, but no changes were observed after the silanization process. This indicates that the chemical oxidation generated a very low density of hydroxyl groups, thereby making the silanization less effective.

Fabrication and stability of a biosensor approach

The described PDMS biofunctionalization approaches were applied to the modification of a photonic Abbe prism based LoC system. Horseradish peroxidase was selected as a model biomolecule. The analytical performance of the resulting modified systems was then tested by carrying out the analysis of H_2O_2 . HRP was chosen because it is a widely used enzyme that exhibits a high turnover number and can be applied with a high number of different mediators. Also, as H_2O_2 is the product of many other enzymatic reactions, HRP catalysis can be coupled in more complex enzymatic systems in order to get a cascade reaction to be applied for signal amplification.

For this aim, photonic LoCs were fabricated by a cast molding process, following a previously reported protocol³⁰. The aldehyde-modified PDMS microchannels obtained after the different modification methods were incubated for 1 hour with 1 mg/mL HRP solution in carbonate buffer pH 8, getting it bound through the amine groups of its lysine residues by forming a Schiff base that is then reduced to a stable

secondary amine with sodiumcyanoborohydride $(\text{NaBH}_3\text{CN})^{31}$. The time of incubation and concentration of biomolecule could change depending on the biomolecule to be immobilized, while the used buffer has the adequate composition for the reaction to take place. The weakly and non-specifically adsorbed enzymes were removed by rinsing the surfaces with a Phosphate Buffered Saline (PBS) solution pH 8 containing Tween 20, a rinsing step commonly applied for this purpose^{32,33}. HRP catalyzes the reduction of H_2O_2 in the presence of 0.5 mM of colorless 2,2'-azino-bis(3-ethylbenzthiazoline-6-sulfonic acid) (ABTS) mediator in acetate buffer pH 5.5, which is in turn oxidized to the green-colored ABTS $^{\bullet+}$ radical cation³⁴ (Figure 11). This cation presents an absorption peak at 420 nm and two secondary peaks at 650 and 720 nm wavelengths. The first one was chosen for the absorbance detection of this enzymatic reaction. Since proteins can easily adsorb on the surface of native PDMS due to their high hydrophobicity⁷, a fourth LoC was modified by direct adsorption of the enzyme under the same experimental conditions applied in the other approaches and tested for comparative purposes.

The modified LoCs were stored for over two months and the operational stability of the immobilized enzyme was studied by calculating the sensitivity along with time. A better stability was expected for those systems selectively modified with the enzyme compared with that one where HRP directly adsorbed. This behavior could be anticipated considering the lack of control of the adsorption process and the fact that adsorbed proteins tend to expose the highest area possible to the surface in order to maximize this interaction, which produced irreversible changes in their structure and conformation and resulted in their extensive unfolding and inactivation³⁵.

As it can be seen in Figure 12, the absorbance at 420 nm increased together with the H_2O_2 concentration for all the tested systems. This increase was linear in the range 0-24.3 μM H_2O_2 and then saturation occurred. A linear fitting was carried out in this range and the analytical parameters were calculated (Table 3). There were no significant differences among the different approaches, but the estimated error was higher for the adsorption approach. The lowest LOD was 0.10 μM H_2O_2 . This result was between 10 and 100 times lower than the previously reported values in similar analytical systems based on the use of HRP as a receptor^{25,36}. In addition, the sensitivity of the modified PhLoC was 150 times better than in other applications using the same system³⁰.

The storage stability of the modified PhLoC systems was studied by calculating their changes in sensitivity with time, as mentioned above (Figure 13). Two different behaviors could be observed. The systems based on the modification with PEG showed a rapid decrease in the sensitivity during the first week, while those based on the PVA modification and chemical oxidation remained more stable for at least one month. However, the latter showed a decrease in the sensitivity after the first month, while the PVA-based system retained 82% of the initial sensitivity after two months.

The present results indicate that the PVA and chemical approaches provide the PhLoC systems with a better analytical performance in terms of both reproducibility and stability. The structural characterization

together with the analytical studies also verify that the PVA-based procedure should be the one chosen for the modification of PDMS with enzymes considering the higher density of functional groups introduced during the modification steps and the longer stability of the resulting analytical PhLoC system.

References

1. Makamba H., Kim J.H., Lim K., Park N., Hahn J.H. Surface modification of poly(dimethylsiloxane) microchannels. *Electrophoresis* 24, 3607-3619 (2003).
2. McDonald J.C., Whitesides G.M. Poly(dimethylsiloxane) as a material for fabrication of microfluidic devices. *Acc. Chem. Res.* 35(7), 491-499 (2002).
3. Gray D.S., Tien J., Chen C.S. Repositioning of cells by mechanotaxis on surfaces with micropatterned Young's modulus. *J. Biomed. Mater. Res., Part A* 66(3), 605-614 (2003).
4. Xia Y., Whitesides G.M. Soft lithography. *Annu. Rev. Mater. Sci.* 28, 153-184 (1998).
5. Huang B., Wu H., Kim S., Zare R.N. Coating of poly(dimethylsiloxane) with n-dodecyl-beta-D-maltoside to minimize nonspecific protein adsorption. *Lab Chip* 5, 1005-1007 (2005).
6. Bai Y. et al. Surface modification for enhancing antibody binding on polymer-based microfluidic device for Enzyme-Linked Immunosorbent Assay. *Langmuir* 22, 9458-9467 (2006).
7. Yasukawa, T., Maekawa, E. Mizutani, F. Immobilization of glucose oxidase on a poly(dimethylsiloxane) layer by using poly(L-lysine) as a polymer backbone. *Anal. Sci.* 25, 1159-1162 (2009).
8. Wong I., Ho C.M. Surface molecular property modifications for poly(dimethylsiloxane) (PDMS) based microfluidic devices. *Microfluid. Nanofluid.* 7, 291-306 (2009).
9. Slentz, B.E., Penner, N.A., Lugowska, E., Regnier, F. Nanoliter capillary electrochromatography columns based on collocated monolithic support structures molded in poly(dimethyl siloxane). *Electrophoresis* 22, 3736-3743 (2001).
10. Slentz, B.E., Penner, N.A., Lugowska, E., Regnier, F. Nanoliter capillary electrochromatography columns based on collocated monolithic support structures molded in poly(dimethyl siloxane). *Electrophoresis* 22, 3736-3743 (2001).
11. Bodas D., Khan-Malek C. Hydrophilization and hydrophobic recovery of PDMS by oxygen plasma and chemical treatment – An SEM investigation. *Sens. Actuators B* 123, 368-373 (2007).
12. Berdichevsky Y., Khandurina J., Guttman A., Lo Y.H. UV/Ozone modification of Poly(dimethylsiloxane) microfluidics channels. *Sens. Actuators B* 97, 402-408 (2004).
13. Sandison, M.E., Cumming, S.A., Kolch, W., Pitt, A.R. On-chip immunoprecipitation for protein purification. *Lab Chip* 10, 2805-2813 (2010).
14. Sui G. et al. Solution-phase surface modification in intact poly(dimethylsiloxane) microfluidic channels. *Anal. Chem.* 78(15), 5543-5551 (2006).
15. Phely-Bobin, T.S., Muisener, R.J., Koberstein, J.T., Papadimitrakopoulos, F. Site-specific self-assembly of Si/SiO_x nanoparticles on micropatterned poly(dimethylsiloxane) thin films. *Synthetic Met.* 116, 439-443 (2001).
16. Efimenko, K., Wallace, W.E., Genzer, J. Surface modification of Sylgard-184 poly(dimethyl siloxane) networks by ultraviolet and ultraviolet/ozone treatment. *J. Colloid Interface Sci.* 254, 306-315 (2002).
17. Chen, H.Y., Lahann, J. Fabrication of discontinuous surface patterns within microfluidic channels using photodefinable vapour-based polymer coatings. *Anal. Chem.* 77, 6909-6914 (2005).
18. Roman, G.T., Hlaus, T. Bass, K.J., Seelhammer, T.G., Culbertson, C.T. Sol-gel modified poly(dimethylsiloxane) microfluidic devices with high electroosmotic mobilities and hydrophilic channel wall characteristics. *Anal. Chem.* 77, 1414-1422 (2005).
19. Roman, G.T., Culbertson, C.T. Surface engineering of poly

(dimethylsiloxane) microfluidic devices using transition metal sol–gel chemistry. *Langmuir* 22, 4445-4451 (2006). 19. Towns, J.K., Regnier, F.E. Capillary electrophoretic separations of proteins using nonionic surfactant coatings. *Anal. Chem.* 63, 1126-1132 (1991). 20. Makamba, H., Hsieh, Y.Y., Sung, W.C., Chen, S.H. Stable permanently hydrophilic protein-resistant thin-film coatings on poly(dimethylsiloxane) substrates by electrostatic self-assembly and chemical cross-linking. *Anal. Chem.* 77, 3971-3978 (2005). 21. Ibarlucea B., Fernández-Sánchez F., Demming S., Büttgenbach S., Llobera A. Selective functionalisation of PDMS-based photonic lab on a chip for biosensing. *Analyst* (2011) DOI: 10.1039/c0an00941e 22. Yu L., Li C.M., Zhou Q., Luong J.H.T. Poly(vinyl alcohol) functionalized poly(dimethylsiloxane) solid surface for immunoassay. *Bioconjug. Chem.* 18(2), 281-284 (2007). 23. Charles P. T. et al. Reduction of non-specific protein adsorption using poly(ethylene) glycol (PEG) modified polyacrylate hydrogels in immunoassays for staphylococcal enterotoxin B detection. *Sensors* 9, 645-655 (2009). 24. Zimmermann J.L., Nicolaus T., Neuert G., Blank K. Thiol-based, site-specific and covalent immobilization of biomolecules for single-molecule experiments. *Nature Protocols* 5(6), 975-985 (2010). 25. Llobera A., Wilke R., Büttgenbach S. Poly(dimethylsiloxane) hollow Abbe prism with microlenses for detection based on absorption and refractive index shift. *Lab Chip* 4, 24-27 (2004). 26. Kozlov, M. Quarmyne, M., Chen, W., McCarthy, T.J. Adsorption of poly(vinyl alcohol) onto hydrophobic substrates. A general approach for hydrophilizing and chemically activating surfaces. *Macromolecules* 36, 6054-6059 (2003). 27. Hair M.L., Tripp C.P. Alkylchlorosilane reactions at the silica surface. *Colloids Surf. A* 105, 95-103 (1995). 28. Mata A., Fleischman A.J., Roy S. Characterization of polydimethylsiloxane (PDMS) properties for biomedical micro/nanosystems. *Biomed. Microdevices* 7(4), 281-293 (2005). 29. Hillborg H. et al. Crosslinked polydimethylsiloxane exposed to oxygen plasma studied by neutron reflectometry and other surface specific techniques. *Polymer* 41, 6851-6863 (2000). 30. Llobera A., Wilke R., Büttgenbach S. Enhancement of the response of poly(dimethylsiloxane) hollow prisms through air mirrors for absorbance-based sensing. *Talanta* 75, 473-479 (2008). 31. Ferreira L., Ramos M.A., Dordick J.S., Gil M.H. Influence of different silica derivatives in the immobilization and stabilization of a *Bacillus licheniformis* protease (Subtilisin Carlsberg). *J. Mol. Catal. B: Enzym.* 21, 189-199 (2003). 32. Zhang, K., Diehl, M.R., Tirrell, D.A. Artificial polypeptide scaffold for protein immobilization. *J. Am. Chem. Soc.* 127, 10136-10137 (2005). 33. Shriver-Lake, L.C. et al. Antibody immobilization using heterobifunctional crosslinkers. *Biosens. Bioel.* 12(11), 1101-1106 (1997). 34. Kadnikova E.N., Kostic N.M. Oxidation of ABTS by hydrogen peroxide catalyzed by horseradish peroxidase encapsulated into sol-gel glass. Effects of glass matrix on reactivity. *J. Mol. Catal. B: Enzym.* 18, 39-48 (2002). 35. Di Risio, S., Yan, N. Adsorption and inactivation behavior of horseradish peroxidase on various substrates. *Colloid Surface B* 79, 397-402 (2010). 36. Tamasko M. et al. An approach to in situ detection of hydrogen peroxide: application of a commercial needle-type electrode. *Physiol. Meas.* 28, 1533-1542 (2009).

Acknowledgements

This work has received funding from the European Research Council under the European Community's Seventh Framework Programme (FP7/2007-2013)/ERC grant agreement no. 209243. The authors thank

Dr. Manuel Gutierrez for his kind help with the AFM study.

Supplementary Files

This is a list of supplementary files associated with this preprint. Click to download.

- [supplement0.docx](#)