

Studies on Clarification of Coal Washery Effluent Using Polymeric Flocculants and Settling Kinetics

Sarika Narayanrao Pimpalkar (✉ sarika@iitism.ac.in)

IIT (ISM): Indian Institute of Technology <https://orcid.org/0000-0002-3653-2012>

Nikkam Suresh

IIT (ISM): Indian Institute of Technology

Gurdeep Singh



IIT (ISM): Indian Institute of Technology

Research Article

Keywords: Flocculation, Kinetics of settling, Turbidity removal, coal sedimentation, Washery water clarification, Polymeric flocculants

Posted Date: March 29th, 2021

DOI: <https://doi.org/10.21203/rs.3.rs-285663/v1>

License:   This work is licensed under a Creative Commons Attribution 4.0 International License. [Read Full License](#)

Abstract

Settling tests were conducted on the washery effluent using three types of flocculants namely cationic (Telfloc-3674F), anionic (Magna-1011) and non-ionic (Nalco-83370 +). For the study purpose coal washery effluent (having pH of 8.72) was collected from a newly commissioned plant-thickener. Tests were conducted by varying the pH of the pulp at three levels of acidic (4.0), alkaline (11.0) and the natural pH (8.72) of the as collected effluent, besides the flocculent dosages varied at four levels (2, 4, 6 and 8gpt) for each of the flocculants stated. The results of these tests, estimated in terms of initial settling rate and turbidity indicated that; among the three flocculants tested Telfloc-3674F and Magna-1011 gave best results as compared to Nalco-83370 + flocculent at a washery water pH 8.72. The effect of molecular weight of the flocculants on settling of solids in effluent has been established in terms of the kinetics with a characteristic number for each of the type of flocculants used.

Introduction

With advancements that have taken place in the field of mining, proportion of fines generation in the ROM coal has gone up appreciably. This resulted in numerous environmental problems related to air-water pollutions. Further, Indian coals possess difficult-to-wash property which needs finer size reductions for improved liberation prior to washing. This has resulted in generation of excess fines in the coal being sent to washing circuits. Coal (hydrophobic) along with other mineral fines (hydrophilic) like shale, slate, clay and several other impurities are generated during stacking, handling, transportation, and dumping at different points in CPP (Duong et al. 2000). Coal washing involves wet processes where coal gets mixed with water, and requires efficient dewatering and clarification techniques. Coal being hydrophobic in nature, at finer sizes the particles remain suspended in water and do not settle even after several days, particularly in tailing ponds. This pollutes the ground water and also deteriorates the agricultural land/crops surround it. Besides this the unclarified, when recirculated to coal washing plants, spoils the overall performance of the operating washery, because of accumulation of colloidal sized particles in excess. These problems are not limited only to the Indian coal washing circuits, but it is noticed globally in all the coal washeries (Moosavirad et al. 2010; Sabah and Erkan 2006; Gupta and Singh 1995; Sarioglu et al 2002).

To get-rid of all these problems, one alternative is to enhance the settling rate of particulate solids using flocculants (Khandal 1985). Polymer flocculants show higher efficiency and acceptability in wastewater/effluent treatments (Bolto and Gregory 2007; Lee et al. 2014; Teh et al. 2016; Dao et al. 2016) especially for removing suspended particulate matter that are accountable for high turbidity (Haiyang et al. 2017). Flocculants are high-molecular long chain water-soluble polymeric compounds that bind the surfaces of the dispersed particles physically and combine them to form agglomerates known as flocs that settle rapidly. The widely used flocculants are; the polyelectrolytes of anionic or cationic or non-ionic types having high molecular weight with different structures of macromolecules which intensify the solid-liquid separations in coal washing plants (Yakovchenko et al. 2019). Long-back Slater and Kitchener reported that the application of certain polymers as flocculants helped in promoting the settling rates of solids in industrial disperse systems (Slater and Kitchener 1966).

Water clarification plays a major role in the overall economics of the coal preparation plants (CPP). As per the present environmental policies no effluent/slurry is allowed to be discharged outside the washery premises. Under these circumstances, water clarification using flocculants will help to abide by the guidelines set by MoEF, GoI, 2010, wherein the CPP are to operate the plants on a closed system water-circulation basis, and limit the fresh water consumption not exceed above 1.5 m³. Nowadays, the washeries are designed for closed-circuit system, where the water used in washing circuits to wash the raw coal is recycled and reused. Since this water detains appreciable percentage of colloidal size coal fines and clay particles, need to be clear-off dirt and contain only negligible amounts of suspended particles. Otherwise, huge volume of water would be required to process the coal. But, the removal of these colloidal fines (or water clarification) from the tailing slurry has posed number of challenges.

As a general norm, fines having size less than 0.50 mm are generally responsible for forming slurry in the washery (Ash and Rao 1972). Thus, an appropriate solid-liquid separation has become an essential part of a coal washing plant. In practice, the prevalent method adopted is sedimentation with aid of flocculants in thickeners, using polymeric flocculants. This method has two significant strictures that evaluate flocculation performance (Oruç et al. 2010).

- i. The first is the low water-turbidity, since water recovered at the thickener overflow is recycled to the plant. The suspended colloidal particles in the recycled water should be at the lowest level, eliminating any negative implications to the process.
- ii. The second is, settling rate of the flocculated particles, has a direct effect on thickener capacity as well as flocculent performance.

Thus, the challenge is dual; precise determination of various properties of the washery water effluent, this includes mineralogy of the gangue particles, physic-chemical properties such as pH, conductivity, pulp density, TDS, alkalinity, hardness etc. besides electro-kinetic properties of the solid matter in washery effluents.

Achieving the lowest water turbidity level while maintaining high settling rate typically influenced and controlled by polymeric flocculent properties, its dosages and the pH value of the washery effluent. Moreover, the efficiency of the process is dependent on the use of accurate type of flocculants (i.e. anionic, cationic and non-ionic polymer) as well as the addition of their dosage (Sabah and Cengiz 2004; Pal et al. 2008).

On the other hand, water is becoming a scarce commodity, and several governmental slogans are heard every day to save water under the government's national policy. Still, the problem of water purification persists and supply of good quality water remains as a major problem. Thus, coal-water slurry handling has become an integral part of a coal beneficiation plant. This is because, the amount of fine-coal tailings generated annually is very high. To overcome the difficulties faced, the alternatives left are:

- i. Development of efficient solid-liquid separation systems,
- ii. Selection and addition of the correct flocculent.

- iii. Understanding of the interaction between the flocculent and the slurry is vital in achieving optimum condition.

In view of the above, in this study the influence of flocculent types, their dosage effects and effect of pH of the pulp on the settling of fine coal fines has been attempted after the physico-chemical and mineralogical characteristics of an effluent collected from a thickener of an operating plant (Dahibari, India).

Materials Used And Their Characterization

2.1 Sample Collection and plant details: Coal washery effluent from a tailing thickener of Dahibari coal washing plant operating under Bharat Coking Coal Limited, Dhanbad, was collected from the feed-well pipe of the thickener. Collection of the effluent sample was made in large capacity plastic containers with their lids fitted air-tight and stored intact as per guidelines given by American Public Health Association (APHA 2012). Among the several containers, one of the container was selected, the slurry was filtered and dried. The solids obtained thereof were analysed for the characterisation studies in detail.

About Dahibari coal washing plant: Dahibari washery was designed for washing of high-ash Indian coals, that are recently classified and categorised as washery grade IV (with 28 to 35% ash) and washery grade V (with 35 to 42% ash). This is a standalone-type coal washery commissioned in the year 2018 with a treatment capacity of 1.6 MTPA of coal that produces small quantity of washed coking coal (of 19% ash) and the power coal (middling) as its final products. Both washed coal (of 19% ash) and the middling (with $33.5 \pm 0.50\%$ ash to captive power plants) are sent to SAIL steel plants. Since the washery was designed to receive coals from different collieries, it falls under the category as NLW (Non-linked washery). Hence the feed ash of raw coal to the washery varies very widely ranging from 28% to 40%. Raw coal crushed to 30-mm is washed with the help of heavy media cyclones and thickeners installed for the collections of comparatively large-sized fraction of fines. The supernatant water of the thickener impounded is re-circulated to the plant while the sludge of the thickener is store in tailing ponds. The satellite location map (latitude=23°72'91.4"N and longitude=86°77'92.0"E) of Dahibari is given in Fig. 1.

2.2 Characterization of Sample: Characterization studies on the collected effluent sample was carried out to know the physico-chemical parameters of slurry viz. pH, conductivity and TDS were measured onsite while the other parameters in the laboratory. The collected effluent showed a natural pH of 8.72 and high turbidity value of 1370 NTU, which may be because of presence of colloidal fines necessitating addition of flocculent for improved clarification. All the physic-chemical properties of the effluent are presented in Table 1. For other characterization studies of coal in effluent, a small amount of slurry was dried at 40°C and the results are presented in Table 2. Details of the major instruments used for characterization studies are mentioned in Table 3.

2.3 Water and Flocculants used: The washery-water slurry of natural pH 8.72 was used to study settling test. To study the effect of pH of pulp (4.0 and 11.0), the same washery-water was induced by addition of required amount of 1N Hydrochloric acid (HCL) supplied by M/s RFCL Ltd., New Delhi, India and 1N Sodium Hydroxide (NaOH) supplied by Merck Specialities Pvt. Ltd., Mumbai, India. For experimental

work three types of flocculants were selected namely viz., Cationic flocculent – Telfloc-3674F (TF), Anionic flocculent - Magna-1011(MF) and Non-ionic - Nalco-83370⁺ (NF). Settling tests were performed by varying each of the above stated flocculants at 3 levels. TF is a medium molecular weight cationic polyacrylamide was supplied by M/s Ion Exchange India Ltd., Patancheru, India. MF is a high molecular weight anionic polyacrylamide supplied by M/s BASF, India. Whereas, NF is a non-ionic polymer supplied by M/s Nalco, India as presented in Table 4. For each test desired amount of freshly prepared flocculent was used after diluting it to 0.1% w/w homogeneous stock solution to study the dosage variations. Fresh flocculent solutions were prepared at an interval two days to improve the precession of results.

Flocculation Tests And Experimental Studies

A total of 36 Settling tests were performed using three different flocculants. For each type of flocculent, its dosages were varied at four levels and for each dosage of the flocculent, three pH levels were studied. In all these tests a fixed pulp solids concentration of 3.0% w/w was kept constant (as per prevailing practice at the plant). All these tests were performed at the room temperature varying between 25 - 30°C. The details of the test conducted along with the levels of the variables studied are summarised in Table 5. Each of these settling test were performed in a 1000 cm³ graduated measuring cylinder as per ASTM (ASTM 2008) standard jar-test method. For homogeneous mixing of slurry, a constant mixing time of 3min was applied to the collected grab sample prior to each tests. The desired amount of flocculent was added to the slurry, followed by manual stirring for 30 sec. The change in the interface heights as a function of time was recorded for plotting of the settling curves. The interface heights of slurry for the chosen time intervals of 0, 15, 30, 45, 90, 120, 180, 300, 600 seconds were noted. Using this data, settling rates were established graphically from the slope of the straight line of settling curve obtained as per standard procedure (Fig.6c). After 600 sec of settling time, an aliquot of the supernatant was taken for the turbidity measurements using turbidimeter.

Discussion On The Results Of Characterization Tests Conducted

The following characterization studies were carried out on the high-ash Dahibari effluent fines:

- a. **Granulometric analyses of coal washery effluent:** The particle size distribution patterns expressed in both differential and cumulative forms (by volume percentages) washery effluent are shown in Figs. 2a and 2b respectively indicating about 80% of the particles are below 60 µm in the effluent (Fig.2b).
- b. **Zeta potential studies:** The zeta potential of the suspension plays an important role in flocculation. It is a measure of surface charge acquired on the particles in washery effluent. The results of Zeta potential of Dahibari washery effluent as a function of pH is shown in Fig. 3. The zeta potential value of the particles at natural pH of 8.72 was 10.3 mV exhibiting positive surface charge at all pH values except at pH 12. The addition of OH⁻ ions (from NaOH) is accountable to revert the positive surface charge into negative at alkaline pH 12 of effluent. The positive surface charge may be due the presence of aluminosilicates along with sodium and potassium. However, in the presence of flocculants at a pH of 8 the value of the zeta potential gets increased to -70.1mV, -69.1mV and -52.8mV for TF, MF and NF

flocculants respectively. According to the ASTM D-4187 Standard Test Method, if the zeta potential of colloids (colloidal particles) in water or waste slurry is above -60mV, the stability of the system is classified as 'perfect' (Sabah and Erkan 2006). Since, the present case zeta potential for the coal slurry was observed to be 10.3mV at the pH 8, this was classified and considered as highly stable condition, suggesting the possibility of increase in settling characteristics through flocculation.

- c. **XRD analysis of coal:** The adsorption of a flocculent depends on the mineralogical assemblages of the suspended particulate matter, in addition to the prevailing aqueous environment i.e., in the present case the quality of effluent collected from the washery. Therefore, it was necessary to identify the gangue mineral components present in the feed coal. The XRD pattern of the washery effluent coal is represented in Fig. 4, which indicates the presence of quartz, kaolinite and muscovite as the gangue minerals present in the order of increasing intensity of XRD.
- d. **TG-DTA analysis of feed coal:** To confirm the results of proximate analysis of coal TG-DTA test were conducted at a heating rate of 10K/min in oxygen atmosphere on the coal washery effluent. The TG-DTA peaks shown in Fig. 5 depicts a drastic weight loss over 300-600°C temperature range in the TGA curve is due to decomposition of carbon, volatile matter and moisture of the coal. Similar observations were also made by Sabah et al. (Sabah et al. 2004).

Results And Discussion

To identifying a most suitable type of flocculent for improved clarification of coal washery effluent, the results of all the jar settling tests conducted have been analyzed in terms of (i) initial settling rates and (ii) the turbidity of the aliquot supernatant liquid. These two responses were determined as stated below:

Estimation of Initial Settling rate: This was determined graphically (as per the standard practice) by plotting the height of the slurry-water interface measured as function of time. The value of the slope of the settling curve estimated graphically in the near straight-line region of initial settling periods is considered as the 'initial settling rate'. This is shown in Fig.6c as a typical example (for a test done at 4gpt of dosage at a pH of 8.72 of the flocculent TF). Together with the settling curve (Fig.6c), a comparison of settling data with the zones noticed in thickeners corresponding to the interfaced seen in a jar test is made in Figs. 6 (a and b).

Suspension Turbidity: Turbidity of the aliquot drawn from the supernatant liquids at the end of 600 seconds were measured by Turbidimeter. These results were used in conjunction with the initial turbidity of the washery effluent to measure the 'Turbidity Removal Efficiency' given as (Osborne 1978; Ozkan and Yekeler 2004; Ozkan et al. 2016):

$$\text{Turbidity removal efficiency, \%} = \left[1 - \frac{T_f}{T_o} \right] * 100 \quad \text{Eq. (1)}$$

Where, T_o - is the initial turbidity (Nephelometric turbidity unit, NTU) of the washery effluent, T_f - is the final turbidity of the supernatant liquid obtained after flocculation at the end 600 sec.

5.1 Effect of flocculent type and its dosages on initial settling rates

In flocculation, the molecular weight of a flocculent affects the performance as it controls the inter-particle bridging mechanism, and so the clarification. Literature cited on this aspect revealed that (Reuter and Hartan 1986; Duong et al. 2000; Negro et al. 2005; Sabah and Erkan 2006; Vajihinejad et al. 2019) higher molecular weight results in

improved bridging mechanism, despite the evidences where, increase in molecular weights beyond certain limit, results in deleterious effects. This in fact may be because; very high molecular weight flocculants generally are more viscous and do not mix properly or get distributed throughout the slurry. This affects the adsorption, which has to be very rapid. In view of this in the present study, three different molecular weight flocculants (of high; MF, medium; TF and low; NF) were selected as specified in Table-4.

Figs.7 (a to c) are plotted to analyse and compare the influence of the three flocculent types (TF, MF and NF) by considering the initial settling rates of the flocs at varied flocculent dosages (varied from 2gpt to 8gpt), for the tests conducted at a constant level of pH in each of these figure. The maximum initial settling rate observed is for the flocculants TF and MF with the initial settling rate values of 0.4178 and 0.3333cm/sec respectively. whereas, with low-molecular weight flocculent NF the highest initial settling rate noticed is 0.2960cm/sec when analysed at a fixed dosage of 8gpt at a natural pH of 8.72. This established clearly the influence of molecular weight and the iconicity of the flocculants studied (Table 4).

Further, the effect of dosage of the flocculants added is also illustrated in these figures, where; an increase in the settling rate of coal (together with mineral impurities) also increases gradually and touches a highest value (Angle et al. 1997; Somasundaran and Das 1998; Sabah and Erkan 2006) with increased flocculent dosage. The variations noticed in the settling rates are significant only after 6gpt of flocculent addition, for all the three types of flocculants tested. However the reason for low settling rates at lower dosages for a given pH may be due to the inadequate concentration of polymer for adsorption onto the surface of the particles (Sabah and Aciksoz 2012; Sabah et al. 2003).

5.2 Influence of pH of effluent on settling rate

The pH value of an effluent plays a significant role on adsorption of a polymer onto the surface of particle and size-growth of flocs in slurry (Stutzman and Siffert 1977; Somasundaran and Das 1998; Yu and Somasundaran 1996; Pefferkorn 1999; Rattanakawin and Hogg 2001; Sabah et al. 2003). Figs. 7 (a to c) are plotted to study the effect pH variations clearly depicts that at natural pH (pH= 8.72), initial settling rates observed are of high values than that of acidic (pH= 4.0) and alkaline (pH= 11.0) pH levels of the effluent. This implies that, in acidic and alkaline pH levels, excess of H^+ and OH^- ions occupy the surface of oppositely charged mineral impurities associated with coal fines and also resist the extension of long-polymer chains in slurry, despite of its high dosages which negatively affects flocculation process & lowers down the rate of settling (Moyakhe et al. 2017).

Incidentally, the cationic polymer (TF) has positive charge patch of quaternary ammonium, sulphonium or phosphonium ions (Vajihinejad et al. 2019) that adsorb through long chain polymer bridging onto the positive charge surface of particles present in effluent. Simultaneously, the negative charge patch of carboxylic group on the anionic polymer (MF) gets adsorbed on the positively charged particles present in the washery effluent through charge neutralization. While, the non-ionic polymer (NF) gets adsorbed through hydrogen bonding or hydrophobic interactions (Littlefair and Lowe 1986; Sabah et al. 2003) during floc formation of the particles present in Dahibari washery effluent. This implies involvement of different mechanisms at different pH ranges in clarification of Dahibari washery effluent. Thus resulting retarded settling rates in acidic and alkaline pH conditions of the effluent. Therefore a natural pH 8.72 is found to be effective for all types of flocculants used in this study to enhance the settling rates.

5.3 Effect of turbidity analogous to settling rate

Since the Dahibari coal washery effluent consisted of kaolinite (clay) and muscovite minerals. Both being flaky/lath shaped particles, do not settle easily and remain suspended, leading to high turbidity of the aliquot. Turbidity of

Dahibari washery gave a value of 1370 NTU at natural pH of 8.72 imparting black colour to the effluent (Table 1). Figures 8 (a to c) shows a maximum turbidity removal of 99.19% (11.1 NTU), 99.28 (9.8 NTU) and 93.20 (93.1 NTU) for TF, MF and NF respectively at 8gpt of floc dosage and natural pH of 8.72. This analogous to the initial settling rates mentioned in section 5.1. A highest turbidity reduction of 9.8 NTU was noticed with MF because of oppositely charged physical bonding between the particles in effluent and the anionic surface charge of flocculent. Besides this, the variations noticed in turbidity results is due to high molecular weight of polymers leading to formation of large sized but less compact flocs, while the low molecular weight polymers show a reverse phenomenon resulting in formation of small and more compact flocs (Gregory 1989; Hogg 2000; Tao et al. 2000; Sabah et al. 2003).

In general, at slow initial settling rates, the colloidal particles in effluent get more time to interact with polymer and also more inter-particle collisions to form strong flocs resulting in more clarity of supernatant. But in the present case, for the cationic and anionic flocculants, even with higher initial settling rates the turbidity removal efficiencies noticed are high.

However figures 8 (d to f) and 8 (g to i) clearly represent that even with reduced initial settling rate values (noticed at acidic and alkaline pH levels) the turbidity removal efficiencies did not improve. This observations is noticed at all the dosage levels of the flocculants. In other words, even with increased flocculent dosage, the turbidity removal efficiency do not meet the high values observed with that of natural pH of 8.72. This is mainly because of the presence of excess of H^+ and OH^- ions that hinder the polymer adsorption activity onto the surface of particles present in Dahibari washery effluent. It can be concluded from figure 8 that high supernatant clarity does correspond to high settling rate.

5.4 Settling kinetics

The effect of flocculants (TF, MF and NF) on clarification of Dahibari effluent has been assessed for the date of natural pH (8.72) using a standard second-order kinetic model given as (Raj 2001):

$$\text{Second Order Rate, } K_2 = \left[\left(\frac{1}{(a-t)} \right) * \left(\frac{x}{(a-x)} \right) \right] \quad \text{Eq.(2)}$$

Where 'a'- is the initial height of effluent in a jar test, and 'x'- is the final interface height of effluent after addition of flocculent measured at time 't'.

From Eq.2, the efficiency of flocculation can be estimated by plotting the second order rate constant K_2 ($\text{cm}^{-1} \text{ sec}^{-1}$) against time-'t'. Gregory (Gregory 2013) described it as second-order rate equation based on collision theory for flocculation.

The Plots shown in Figures 9 (a to c) represent the settling curves at varied flocculent dosages for three different flocculants (TF, MF and NF) obtained at the natural pH of Dahibari washery effluent ($\text{pH} = 8.72$). Figures 10 (a to c) represent their corresponding second order kinetic plots. It can noticed from the settling curves of TF and MF that, all the curves show almost a linear variation with time upto 90sec, and then deviate with prolonged settling time, finally to remain constant after 120 sec of settling time. Whereas, the low molecular weight flocculent NF although shows the linearity in settling upto 90sec, but an exponential variation in settling is noticed till 240sec of settling time which eventually tends to an asymptotic value i.e. after 240sec of time.

In Figures 10 (a to c), the discrete settling rate constants ($\Delta h/\Delta t$) estimated at a different settling durations are plotted against time. This was felt necessary because, most of the settling curves overlapped each other indicating almost similar settling pattern in Figs.9 (a to c). However, the plots shown in Figs. 10 (a to c) clearly depict a distinguishable variations in their linearity following the second order kinetic settling rate for all the three types of flocculants tested. It is interesting to note that, from the slope of these plots, the plotted lines converge and overlap each other with decreased molecular weight of flocculants. This implies the dosage variations made with the low molecular weight flocculent (NF) is marginal and insignificant.

Variation in rate constant with flocculent dosage:

Further, observing to the slopes of the straight lines shown in Figs. 10 (a to c) with a changed flocculent dosages, their slopes were found to increase with the addition of flocculent quantity (gpt.). Higher flocculent dosages gave higher slope values and vice-versa. The variation in slopes noticed is also dependent on the type of flocculent and its molecular weight. Now to understand the effect of flocculent dosage on overall settling rate, Figure 11 has been plotted by taking dosage in gpt (on abscissa) against the value of K_2 (in ordinate) for a given flocculent. In this case also a linear variation of K_2 with the flocculent dosage is observed. The values of the slopes of the lines shown in this plots can be taken as the 'characteristic number' which is dependent of the type and molecular weight of the flocculent when tested at a pH of 8.72 for the Dahibari washery effluent. In other words, the values of these characteristic numbers given as 1.9945 for TF (cationic), 1.229 for MF (anionic) and 0.249 for NF (non-ionic) flocculent types.

5.5 Characterization of effluent coal and flocs

5.5.1 Particle size analysis of effluent coal and flocs

The particle size analysis performed by laser beam particle size-analyzer on the as obtained effluent sample of Dahibari washery and also of the flocculated flocs obtained with 8 gpt of dosage at natural pH of 8.72 using three different types of flocculants (anionic, cationic and non-ionic) are shown in Figs. 12 (a and b) for comparison purpose. Figure 12a represents differential plots in percent volume. Looking at the peak areas of the plots, the peaks obtained with TF & MF overlap on to each other indicating similar performances. Fig. 12b shows that the values for D_{10} , D_{50} and D_{90} percent passing sizes of flocs and also of the feed effluent collected from Dahibari washery. The sizes obtained with TF and MF flocs are bigger and overlap, this supported their high initial settling rate study mentioned in section 5.1. The particle size distribution of the washery effluent and other minerals particles was observed in the range of 4.4 to 142 μm , this size range of particles in effluent get increased to 52 to 327 μm for TF, 45 to 300 μm for MF and 19.7 to 169 μm for NF which indicate formation of flocs after flocculation. These observations are in accordance with that of Gungoren et al ([Gungoren et al. 2017](#)).

5.5.2 FTIR analysis of effluent coal and flocs

Figure 13 is the result of FTIR analysis study of the washery effluent and flocculated flocs. The peaks of these plots show only the presence of inorganic Si-O bending vibrations in the region of 1100-1000 cm^{-1} ([Zhichao et al. 2017](#)) subsequently extended its symmetric stretching vibration peaks of Si-O appeared at 802 cm^{-1} which shows its bending vibration at 470 cm^{-1} . The peaks in FTIR spectra of coal between 1100 and 400 cm^{-1} can be assigned to clay minerals (Kaolinite) and quartz, ([Saikia et al. 2007](#)). The areas of these spectrum showed noticeable deep stretched peaks after flocculation with polymers (TF, MF and NF) in the present study. The transmittance

percentages of Dahibari effluent coal flocs gets shifted upward above the effluent transmittance values after flocculation indicating adsorption of polymers to the inorganic (clay, quartz) associated with the coal surface.

Conclusion

- Characterization studies conducted on Dahibari washery effluent by various methods indicated effluent is of highly heterogeneous nature witness from its physico-chemical properties.
- The collected effluent showed presence of colloidal fines with D80 percent passing size=60 μm which results in high turbidity value of 1370 NTU. Thus hindered the natural settling of coal particles in thickener when observed at a natural pH of 8.72 of effluent without the addition flocculent. This lead to conclude that addition of flocculent as a necessary step.
- The results of the flocculation tests indicated that, all the three flocculants tests gave satisfactory results for clarification of the water of Dahibari washery effluent. However, among the three flocculants tested, the cationic (TF) and anionic (MF) polymer flocculants gave better results in terms of initial settling rates and the measured turbidity values.
- Second order kinetic rate constants estimated elaborate the results of effective clarification occurred between polymer flocculants and the suspended particles of Dahibari effluent.
- The order of effectiveness of polymer flocculants is $\text{TF} > \text{MF} > \text{NF}$. The overall results of the study indicated that, the TF and MF are most suitable for clarification of Dahibari coal washery effluent to reutilize the treated water in coal washing circuits and to reduce the fresh water consumption for coal washing process.

Declarations

Ethical Approval

The authors of this paper hereby confirm that all the procedures described, tests performed, studies conducted, data presented and the interpretations made thereof on data are in accordance with ethical standards of the institution. However the site map of the Dahibari washery presented and the thickener diagram (Fig. 6a) from the website for which the reference has been cited.

Consent to Participate

Not Applicable.

Consent to Publish

All the authors of this paper hereby give their consent publish the contents of the paper after its peer review. Authors have no objection in publishing the data or analytical contents of the paper in the journal.

Availability of data and materials

The material was obtained officially from the Dahibari coal washery, BCCL, Dhanbad after taking the consent from the washery management. The data presented are results of the tests conducted in the laboratory using a 1000 ml jar test as per standard practice.

Competing interest

The authors hereby declare that there is no competing interests.

Funding

This research did not receive any specific grant from any of the funding agencies.

Authors contribution

Ms Sarika Pimpalkar, the first author of this paper has carried out all the experiments in the laboratory under the supervision of Prof Nikkam Suresh and Prof Gurdeep Singh. The supervisors have helped in designing of the experiments, analysis of the data and also in correcting the draft copy of this research paper.

Acknowledgements

The authors wish to express their appreciation towards the necessary facility and support provided by the Department of Fuel, Mineral and Metallurgical Engineering and Department of Environmental Science and Engineering, Indian Institute of Technology (Indian School of Mines), Dhanbad, for execution this research work. The authors also express their gratitude to Dahibari Washery Management, BCCL for providing the washery effluent for the study.

References

American Public Health Association (2012) Standard methods for the examination of water and wastewater (22nd ed). Washington, D.C.

American Society for Testing Materials (2008) Standard practice for coagulation-flocculation jar test of water (D2035-08).

Angle CW, Smith-Palmer T, Wentzell BR (1997) The effects of cationic polymers on flocculation of a coal thickener feed in washery water as a function of pH. J Appl Polym Sci 64(4):783-789.

Ash PN, Rao RRS (1972) Studies on coal preparation in India. Dhanbad: Central Fuel Research Institute.

Bolto B, Gregory J (2007) Organic polyelectrolytes in water treatment. Water Res 41:2301–2324. doi.org/10.1016/j.watres.2007.03.012

Dao VH, Cameron NR, Saito K (2016) Synthesis, properties and performance of organic polymers employed in flocculation applications. Polym Chem 7:11–25. doi.org/10.1039/c5py01572c

- Das B, Prakash S, Biswal SK, Reddy PSR (2006) Settling characteristics of coal washery tailings using synthetic polyelectrolytes with fine magnetite. *J S Afr I Min Metall* 106:707-712.
- Duong C, Choung J, Xu Z, Szymanski J (2000) A novel process for recovering clean coal and water from coal tailings. *Miner Eng* 13(2):173–181.
- Gregory J (1989) Fundamental of Flocculation. *Crit Rev Environ control* 19(3):225-230.
- Gregory J (2013) Flocculation Fundamentals. *Encyclopedia of Colloid and Interface Science*, ed. T. Tadros, Springer-Verlag Berlin Heidelberg 459-624. doi:10.1007/978-3-642-20665-8
- Gungoren C, Baktarhan Y, Kursun I, Ozkan SG, Ozdemir O (2017) Determination of floc size and strength of fine coal tailings using laser diffraction technique. *Int Symposium Mining Environ (ISME conference)*, 27-29 September 2017, 609-16 Bodrum/Turkey.
- Gupta RK, Singh G (1995) Water pollution profile of coal washeries. *Pollut Res* 14(2):203-213.
- Haiyang X, Jing L, Renjie F, Cheng R, Wang S, Zhang J (2017) Flocculation of coal washing wastewater using polysaccharide produced by *Paenibacillus mucilaginosus* WL412. *Environ Sci Pollut Res* (2017) 24:28132–28141. doi 10.1007/s11356-017-0340-4
- Hogg R (2000) Flocculation and dewatering. *Int J Miner Process* 58:223-236.
- IS 2490-1 (1981) Tolerance limits for industrial effluent. New Delhi: Bureau of India Standards (BIS).
- Kapse G, Patoliya P, Samadder SR (2017) Characterisation of coal washery effluent and optimization of coagulation behaviour of *Moringa oleifera* seed as a coagulant. *Environ Monit Assess* 189:133. doi 10.1007/s10661-017-5844-3.
- Khandal RK (1985) Effect of coagulants on flocculation of coal fines by polymer flocculants. *Proc. Indian natn Sci Acad* 51:863-871.
- Lee CS, Robinson J, Chong MF (2014) A review on application of flocculants in wastewater treatment. *Process Saf Environ Prot* 92:489–508. doi.org/10.1016/j.psep.2014.04.010
- Littlefair MJ, Lowe NRS (1986) On the selective flocculation of coal using polystyrene latex. *Int J Miner Process* 17:187-203.
- Moosavirad SM, Shankara M, Janardhana MR (2010) Geochemistry of coal washery effluents in Zarand region, Kerman province, South-east of Iran. *Asian J Environ Sci* 5(2):144-148.
- Moyakhe DM, Campbell QP, Fosso-Kankeu E (2017) The effect of flocculant type on settling properties of fine coal tailings. 9th Int'l Conference on Advances in Science, Engineering, Technology & Waste Management (ASETWM-17) Nov. 27-28, 2017 Parys, South Africa.

- Negro C, Blanco A, Fuente E, Sanchez LM (2005) Influence of flocculant molecular weight and anionic charge on flocculation behaviour and on the manufacture of fibre cement composites by the Hatschek process. *Cement and Concrete Research* 35(11):2095-2103. DOI: 10.1016/j.cemconres.2005.03.004
- Oruç F, Ozgen S, Sabah E (2010) An enhanced-gravity method to recover ultra-fine coal from tailings: Falcon concentrator. *Fuel* 89(9):2433-2437.
- Osborne DG (1978) Recovery of slimes by a combination of selective flocculation and flotation. *Miner Process Extr Metall* 87:189-193.
- Ozkan A, Oner B, Onen V, Duzyol S (2016) Flocculation of coal suspension with mono/dual polymer systems and contribution of Ca(II)/Mg(II) ions. *Sep Sci Technol* 51(1):106-114.
- Ozkan A, Yekeler M (2004) Coagulation and flocculation characteristics of celestite with different inorganic salts and polymers. *Chem Eng Process* 43:873– 879.
- Pal S, Sen G, Karmakar NC, Mal D, Singh RP (2008) High performance flocculating agents based on cationic polysaccharides in relation to coal fine suspension. *Carbohydr Polym* 74:590– 596.
- Pefferkorn E (1999) Polyacrylamide at solid/liquid interfaces. *J Colloid Interface Sci* 216:197-220.
- Raj G (2001) *Advanced Physical Chemistry* 677-680 25th ed. Meerut, UP/India Goel Publishing House.
- Rattanakawin C, Hogg R (2001) Aggregate size distributions in flocculation. *Colloid Surf A- Physicochem Eng Asp* 177:87-98.
- Reuter JM, Hartan HG (1986) Structure and reaction kinetics of polyelectrolytes and their use in solid-liquid-processing. *Aufbereitungs-Technik* 11:598– 607.
- Sabah E, Cengiz I (2004) An evaluation procedure for flocculation of coal preparation plant tailings. *Water Res* 38:1542– 1549.
- Sabah E, Erkan ZE (2006) Interaction mechanism of flocculants with coal waste slurry. *Fuel* 85:350– 359.
- Sabah E, Ersoy B, Cengiz I (2003) Flocculation mechanism of coal preparation plant tailings with various type polymers. *Proceedings of the X. Balkan Mineral Processing Congress* 292-299, 15-20 June 2003, Varna-Bulgaria.
- Saikia BK, Boruah RK, Gogoi PK (2007) FT-IR and XRD analysis of coal from Makum coalfield of Assam. *J Earth Syst Sci* 116(6):575– 579.
- Sarioglu M, Cebeci Y, Beyazit N (2002) Investigation of the effects of some operating parameters using anionic and cationic flocculants for removing solid material in the lignite. *Asian J Chem* 14(1):388– 394.
- Slater RW, Kitchener JA (1966) Characterization of flocculation of mineral suspensions by polymers. *J Discussions Faraday Soc* 42:267-75.

Somasundaran P, Das KK (1998) Flocculation and selective flocculation – an overview. In Proceedings of 7th International Mineral Processing Symposium (Innovation in mineral and coal processing), ed. AS Onal, G Celik, MS Istanbul 81–91 Turkey, Balkema.

Tao D, Groppo JG, Parekh BK (2000) Enhanced ultrafine coal dewatering using flocculation filtration processes. *Miner Eng* 2:163-171.

Teh CY, Budiman PM, Shak KPY, Wu TY (2016) Recent advancement of coagulation-flocculation and its application in wastewater treatment. *Ind Eng Chem Res* 55:4363–4389. doi.org/10.1021/acs.iecr.5b04703

Vajihinejad V, Sarang P, Gumfekar, Bazoubandi B, Najafabadi ZR, Soares JBP (2019) Water soluble polymer flocculants: Synthesis, Characterization and performance assessment. *Macromol Mater Eng* 304(2):1-43.

Wakeman RJ. Thickners. doi: [10.1615/AtoZ.t.thickeners](https://doi.org/10.1615/AtoZ.t.thickeners) as appeared in website: [https:// thermopedia.com/content/1198/](https://thermopedia.com/content/1198/)

Yakovchenko MA, Pinchuk LG, Kolosova MM, Filipovich LA, Masaev VY (2019) Intensification of wastewater treatment processes during coal enrichment using modified polyacrylamide flocculants. *IOP Conf Ser: Earth Environ Sci* 224:1-6. 012051 IOP Publishing. doi:10.1088/1755-1315/224/1/012051

Yu X, Somasundaran P (1996) Role of polymer conformation in interparticle-bridging dominated flocculation. *J Colloids Interface Sci* 177:283-287.

Zhichao Y, Wang W, Shengyu L (2017) Flocculation of coal waste slurry using bioflocculant produced by *Azotobacter chroococcum*. *Energy Fuels* 31(2):1460-1467.

Tables

Table 1: Physico-chemical characterization of Dahibari washery effluent sample

Parameter	Dahibari washery effluent	Permissible Discharge Limit IS:2490 (1981)
Colour	Black	Colourless
pH	8.72	5.5-9.0
Temperature, °C	29.4	< 40
Conductivity, µS/cm	386	-
Turbidity, NTU	1370	-
COD, mg/L	300	250 mg/L
Oil & Grease, mg/L	5.2	10.0 mg/L
Total Hardness as mg/L (Ca+Mg)CO ₃	310	-
Calcium Hardness as mg/L CaCO ₃	306	-
Total Alkalinity as mg/L CaCO ₃	340	-
Total solid, mg/L	7521	-
Total suspended solids, mg/L	7120	-
Total dissolve solids, mg/L	401	2100 mg/L
Chloride as mg/L NaCl	450	1000 mg/L
Fluoride, mg/L	1.15	-
Sulphate as mg/L	144	1000 mg/L
Nitrate as mg/L	2.76	-
Iron (Fe), mg/L	1.7	-
Aluminium (Al), mg/L	0.2	-
Copper (Cu), mg/L	0.1	3 mg/L
Lead (Pb), mg/L	BDL	0.1 mg/L
Zinc (Zn), mg/L	0.8	15 mg/L
Cadmium (Cd), mg/L	BDL	2 mg/L
Arsenic (As), mg/L	BDL	0.2 mg/L
Chromium	BDL	2 mg/L

BDL - Below Detection Limit i.e. -0.001 mg/L

Table 2: Characterization of Dahibari effluent coal

Properties	Unit	Values
Proximate Analysis (Air dried basis)		
Total Ash content,	%	44.96
Volatile matter	%	17.38
Moisture	%	1.91
Fixed carbon	%	35.75
Ultimate Analysis (Air dried basis)		
Carbon	%	33.26
Hydrogen	%	7.56
Nitrogen	%	13.90
Sulphur	%	0.036
Oxygen	%	0.28
Other properties		
GCV# _(EB)	Kcal/kg	3967.2
Specific Gravity	kg/m ³	1568.0
LTGK Grade	-	G12
Loss of Ignition (LOI),	%	55.04
Particle size (D80p),	µm	60
Pulp density (solid concentration) (as received basis)	% w/w	3.0
Major gangue mineral	Kaolinite, quartz, muscovite	

Goss Calorific Value estimated under equilibrated condition (at Temp=40°C and RH=60%)

Table 3: Major Equipment used for characterization

Sl.No.	Name of Equipment	Make	Model No.	State of Origin	Supplier	Type of Analysis
1	Multi-parameter Tester (Water Proof)	Eutech	pH Testr 30	Singapore	M/s Excel International, Kolkata, India	Physical parameter characterization (pH, Temp. conductivity, TDS)
2	Turbidimeter	Eutech	TN-100	Singapore	M/s, Science world, Nagpur, India	Turbidity
3	Photometer	Palintest	Photometer 7100	UK	M/s, International Trade Links Instrumentation Pvt. Ltd., Kolkata, India.	Chemical Parameter (Hardness, Alkalinity, Chloride, Nitrate, sulphate)
4	Atomic Absorption Spectrophotometer	Thermo Fisher	iCE3300 system GFS33	US	M/s, Thermo Fisher Scientific India Pvt. Ltd., Kolkata.	Fe, Al, Cu, Pb, Zn, Cd, As
5	Particle size analyser	Malvern	Hydero2000MU	UK	M/s, Aimil Limited, Kolkata.	Size of coal & coal flocs
6	Thermogravimetric analyser	ELTRA Elemental Analyzers	EltraTGA Thermostep	Germany	Verder Scientific Private Ltd., Kolkata, India	Proximate analysis
7	CHNS analyzer	German	ElementarVario EL-III, S.No.-1101404	India	Elementar India Pvt. Ltd., Gurgaon, India	Ultimate Analysis
8	Bomb calorimeter	LECO	AC-350	USA	IR Technology Services Pvt. Ltd., Kolkata, India	GCV & grade
9	Thermal analyzer	NETZSCH,	Jupiter STA 449F3	Germany	NETZSCH Technologies India Pvt. Ltd. Kolkata, India	TG-DTA analysis
10	XRD analyzer	Rigaku	Smart Lab Studio IIX64x4.3.177.0 IDNo.BD69000287-01	Japan	IR Technology Services Pvt. Ltd., Kolkata, India	XRD analysis
11	FTIR spectrophotometer	Perkin Elmer	Spectrum 2.0	US	Perkin Elmer (India) Pvt Ltd., Thane (MH), India.	FTIR analysis
12	Zeta Meter 4.0 with a microprocessor		Version 1.4 Rev 2c	Verginia	M/s Orbit Research Associates Pvt. Ltd., Delhi, India	Electrokinetic measurements (Zeta potential)

Table 4: Properties of the polymers

Name	Telfloc3674F	Magna1011	Nalco83370 ⁺
Type	Cationic	Anionic	Non-ionic
Charge density	Medium to high charged	Medium to high charged	Low to medium charged
Molecular Weight	Medium	High	Low
Supplier	Ion Exchange India (Ltd.), Patancheru, India	BASF, India	NALCO, India

Table 5: The summary of the tests carried out their levels studied

Variable studied					
Sl No	Category	Pulp density, % (w/w)	Floc Dosage, gpt	pH of Pulp	No. of Tests
1	Telfloc3674F (Cationic)	3	2, 4, 6, 8	8.72	4
			2, 4, 6, 8	4.00	4
			2, 4, 6, 8	11.0	4
2	Nalco-83370 ⁺ (Non-Ionic)	3	2, 4, 6, 8	8.72	4
			2, 4, 6, 8	4.00	4
			2, 4, 6, 8	11.0	4
3	Magna1011 (Anionic)	3	2, 4, 6, 8	8.72	4
			2, 4, 6, 8	4.00	4
			2, 4, 6, 8	11.0	4
Total Tests conducted					36

Figures

Please see the supplementary files section to view the figures.

Figure 1

Please see the supplementary files section to view the figures.

Supplementary Files

This is a list of supplementary files associated with this preprint. Click to download.

- [Figures.docx](#)