

Table 3. Load at fracture (mean values \pm standard deviations) for premolars with CEC or TEC assessed in the Instron Universal Testing Machine

Tooth type (n=10)	Load at fracture (N)		P value
	CEC	TEC	
single-rooted premolars	926.90 \pm 194.97	888.57 \pm 165.73	0.64
two dental root premolars	665.09 \pm 168.74	630.95 \pm 159.81	0.88